



**Polyalphaolefin (PAO) 7 cSt - Option B**  
**PRODUCT INFORMATION**  
**(Axxess PAO 7 – Option B)**

Typical Properties	Specification Range	Test Method
Specific Gravity 15.6 (60°F)	0.810 – 0.840	ASTM D-4052
Viscosity Index	142 - 147	ASTM D-2270
Viscosity cSt 100°C	6.9 – 7.4	ASTM D-445
Viscosity cSt 40°C	35 - 43	ASTM D-445
Viscosity cSt -40°C	14,000 max	ASTM D-445
Pour Point °C	-40 / -45	ASTM D-97
Flash Point °C	255 - 270	ASTM D-92
Neutralizing Number (TAN), mg KOH/g	0.002 – 0.005	ASTM D-974
Refractive Index @ 20°C	1.4612 – 1.4628	
Bromine Number, g Br /100g	0.20 max	IP-129
Noack Volatility 250°C, 1 hr, %wt., Evap	2.2 – 4.0	-/DIN 51581
% Transmission@ 440 nm	>98	
Color	0.5 max	ASTM D-1500
Appearance	Clear & Bright	Observation
Typical Properties	Unit Value	Test Method
Cold Crank Simulator, mPa s (cP)		D-5293
-25 °C	1,750	
-30 °C	3,020	
-35 °C	5,070	
IBP (1%), °C	454	
FBP (99.5%), °C	648	
Air Release, min	1.3	
Aniline Point, °C	133.4	1

Date 1/15/2010

**Note:** Information provided on this sheet is for informational purposes only and is considered to be accurate at the date of printing. However, since Axxess Chemicals has no influence on the use, processing and application of the product, Axxess Chemicals can accept no responsibility whatsoever on this respect and the buyer can derive no rights there from. Customers are advised to test the product in advance to make certain it is suitable for their particular production conditions and assumes all responsibilities arising from the use of the products and the information related thereto. It is also the User's obligation to comply with all applicable laws and regulations. No statement made in this publication shall be construed as a permission, recommendation or authorization given or implied to practice any patented invention without a valid license.

**Axxess Chemicals, LLC, 522 Highway 9 North, Manalapan, New Jersey 07726 USA**  
**Telephone: 877-299-3772 Fax: 732-536-9611**  
**www.axxesschemicals.com**