



Polyalphaolefin (PAO) 8 cSt - Option A
PRODUCT INFORMATION
(Axxess PAO 8 – Option A)

Routine Properties	Specification Range	Test Method
Viscosity cSt 100°C	7.7 – 8.0	ASTM D-445
Viscosity cSt -40°C	24,000 max	ASTM D-445
Pour Point °C	-50 max	ASTM D-97
Flash Point °C	245 min	ASTM D-92
Specific Gravity 15.6/15.6°C (60/60°F)	0.830 – 0.834	ASTM D-4052
Bromine Number, g Br ₂ /100g	0.4	IP-129
Total Acid Number, mg KOH/g	0.01	ASTM D-974
Moisture, ppm	25 max	ASTM D-3401
Noack Volatility 250°C, 1 hr, %wt., Evap	4.0 max	DIN 51581
Color	0.5 max	ASTM D-1500
Typical Properties	Typical	Test Method
Appearance	Clear & Bright	Observation
Viscosity, cSt, 40°C	45 - 49	ASTM D-445
Viscosity, cSt, 125°C	4.9	ASTM D-445
Viscosity, cSt, 150°C	3.3	ASTM D-445
Viscosity, cSt, 200°C	2.1	ASTM D-445
Viscosity, cSt, -18°C	1,605	ASTM D-445
Viscosity Index	136	ASTM D-2270
Density (lb/gal)	6.93	
Molecular Weight	596	GC (Calculated)
DSC, Oxidative Onset Temperature, °C	191	
DSC, Energy kJ/g	13.8	
Aniline Point, °C (F°)	123.3 (254)	
Dielectric Constant, 23°C, 1.0 & 1000 KHz	2.122	

Date 1/15/2010

Note: Information provided on this sheet is for informational purposes only and is considered to be accurate at the date of printing. However, since Axxess Chemicals has no influence on the use, processing and application of the product, Axxess Chemicals can accept no responsibility whatsoever on this respect and the buyer can derive no rights there from. Customers are advised to test the product in advance to make certain it is suitable for their particular production conditions and assumes all responsibilities arising from the use of the products and the information related thereto. It is also the User's obligation to comply with all applicable laws and regulations. No statement made in this publication shall be construed as a permission, recommendation or authorization given or implied to practice any patented invention without a valid license.

Axxess Chemicals, LLC, 522 Highway 9 North, Manalapan, New Jersey 07726 USA
Telephone: 877-299-3772 Fax: 732-536-9611
www.axxesschemicals.com